

FEATURES

Advantages:

- Deep penetration into timber pores
- Reinforces and strengthens timber
- Excellent timber sealer
- Timber preservative
- Easily mixed
- Two Pack: 1:1 Mix Ratio
- Recoatable with Single Pack or Two Pack varnish or high performance coatings system

RECOMMENDED USES

Typically used for:

- All timber surfaces, including timber immersed in fresh or sea water
- Everseal provides the initial pre-treatment of timber surfaces prior to a suitable coating system being applied
- Preserves timber against staining and decay due to fungal attack
- Helps to prevent attack from white ants and other boring insects
- Used to control distortion, cracking and shrinkage of timber
- To limit water penetration particularly into the timber end grain

SPECIFICATION DATA

Coating Type:	Polyamide Cured Epoxy
Colour:	Off Clear
Packaging:	2 litre and 8 litre
	Two component
Mix Ratio:	1:1 by volume
Availability:	Australia only
Gloss:	Sheen at saturation
Flash Point:	27°C Setaflash
Thinner:	Altex Thinning Solvent #12
Pot Life:	8 hours at 25°C
Induction Time:	10 minutes at 25°C
Shelf Life:	12 months
Storage:	Store under cool dry conditions

Density:	0.93 kg per litre
Volume solids (mixed):	31 %
Theoretical Coverage Rate:	12.4 sq. metres per litre at 25 microns dry (porous surfaces will typically reduce this to half the theoretical spreading rate)
Recommended Film Thickness Per Coat:	80 microns wet to obtain 25 microns dry
Application:	Spray, Brush or Roller
Dry Time (at 25°C / 50% RH):	
Touch Dry:	1½ hours
Hard Dry:	3 hours
• Minimum Recoat:	2 hours with itself
•	12 hours - other coatings
• Maximum Recoat:	5 days with itself & other epoxies
	36 hours with other coatings, including single pack products (with light sanding)

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Oil or grease should be removed in accordance with AS1627.1 solvent cleaning.

Wooden Surfaces:

Thoroughly sand with non-stearate 80-120 grit paper.

Use a cross-sanding pattern to create a clear surface profile.

Dedust thoroughly.

DIRECTIONS FOR USE

Mixing:

Everseal is a two component product supplied in 2 litre and 8 litre kits which contain the correct ratio of ingredients.

Power mix the base portion first to obtain a smooth homogeneous condition. After mixing the base portion, slowly add the converter whilst continuing to agitate at slow speed. After addition of the converter is complete, continue to mix slowly until homogeneous.

The Pot Life of the mixed material is 8 hours at 25°C. Higher temperatures will reduce the working life of the coating; lower temperatures will increase it.

Thinning: Thinning is not normally required.

Clean-up: Use Altex Thinning Solvent #12

Application:

Application by brush or roller is the preferred method; however for large areas spray equipment may be used.

Apply sufficient coats to fill all porous areas of timber. Adequately coated wood will exhibit a sheen, porous surfaces not yet fully sealed will exhibit a dry look.

Apply extra coats to end grains and joins, as these areas require special attention.

Do not use mixed product after the pot life has elapsed, even if the mixed product appears to be usable.

PRECAUTIONS

For industrial use only: Read and follow all the caution statements on this Product Data Sheet, the product label and the Safety Data Sheet (SDS) for health and safety information prior to use.

Everseal is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

WWW.ALTEXBOATPAINT.COM

Head Office New Zealand Altex Coatings Ltd

91-111 Oropi Road
Greerton, Tauranga 3112

Ph: +64 7 541 1221
Fax: +64 7 541 1310

Head Office Australia Resene Paints (Aust) Ltd Industrial & Marine Division

7 Production Avenue, Molendinar
Queensland 4214

Ph: +61 7 5512 600
Fax: +61 7 5512 697

DISCLAIMER

The information in this datasheet is provided as a guide only and is provided without warranty, implied or otherwise. It is your responsibility to determine the suitability of any information or product for the use contemplated. Conditions of use, application and the substrate are beyond our control so no liability whatsoever (whether as to coverage, performance, injury or otherwise) is accepted for the information contained herein.

Data sheets may change from time to time and it is your responsibility to ensure you have the latest product datasheet and material safety data sheet from your supplier. Check the data sheet date with the listings at www.altexcoatings.com
Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.