



Regatta[®] Gloss Enamel

Reinforced Alkyd Enamel

FEATURES

- High gloss enamel finish
- Superior, "long oil" Marine quality
- Good weathering properties
- Excellent gloss retention
- Good application characteristics
- Compatible with Altex Flattening Paste to reduce the gloss for interior colours
- May be modified with the addition of Regatta 2K Additive to speed up cure and enhance overall performance. This effectively creates a "Two Pack" finish coat. (see overleaf)

RECOMMENDED USES

Regatta Gloss Enamel is designed for use as the finish coating for the Single Component Marine topsides systems.

Regatta Gloss Enamel can be used on :

- Canoes
- Tenders
- Dinghies
- Trailer yachts
- Power boats
- For signwriting
- Boot stripes
- For upgrading existing enamel systems, subject to correct preparation and undercoating
- And numerous other DIY projects requiring a high-quality enamel finish coat.

SPECIFICATION DATA

Generic Type:	Modified Reinforced Alkyd
Colour:	Refer Altex Yacht & Boat Colour Chart for standard colours. Also available as a custom tint.
Packaging:	Standard: 1 and 4 litre packs NZ: 500ml cans
Gloss:	High Gloss
Flash Point:	35°C
Thinner:	Spray: Altex Thinning Solvent #53 Brush / Roller: Altex Thinning Solvent #45
Storage:	Store under cool, dry conditions

Density:	1.21 kg per litre
Volume Solids:	50%
Theoretical Coverage Rate:	10 sq metres per litre at 50 microns dry
Recommended Film Thickness Per Coat:	80-100 microns wet to obtain 40-50 microns dry
Application:	Spray, brush or roller
Dry Times (50 µm DFT / 25°C / 50% RH):	Touch Dry: 1½ hours Hard Dry: Overnight
Recoat Time (50 µm DFT / 25°C / 50% RH):	Recommended: Overnight (maximum 5 days without sanding)

SURFACE PREPARATION

Regatta Gloss Enamel is designed to be applied over AY&B Surfacer Undercoat, or aged, sanded existing enamel systems.

All surfaces must be clean and dry before application of Regatta Gloss Enamel. If the previous coating is aged more than one (1) week it should be thoroughly sanded and/or cleaned with Altex C50 Surface Cleaner prior to application of Regatta Gloss Enamel.

All exposed substrate should be primed with an appropriate primer, and subsequently undercoated to achieve a smooth, paintable surface.

DO NOT sand using stearate coated sandpaper as these may adversely affect the adhesion of subsequent coatings.

DIRECTIONS FOR USE

Mixing:

Regatta Gloss Enamel is a single component product that requires thorough mixing and careful thinning before use.

Thinning:

For spray application Regatta Gloss Enamel should be thinned 15% to 30% with Altex Thinner #53.

For brush application thin 5% to 15% with Altex Thinner #45

Acceleration:

In cooler conditions, the addition of Regatta 2K Additive will accelerate the cure of Regatta Gloss Enamel. Depending on addition rate, it will reduce dust free times by up to 50%. Other benefits are:

- Increases the hardness of the cured film.
- Reduces time to be able to mask out areas.
- Converts to a harder cross-linked film
- Increases flow and ultimate gloss level

Refer to the Regatta 2K Additive Data Sheet for further information.

Application:

Regatta Gloss Enamel may be applied by spray, brush or roller.

Suggested spray equipment is:

Air Spray	<i>Graco</i> - Delta Air Spray; 1.1 - 1.4 mm Fluid Nozzle <i>De Vilbiss</i> - JGA gun, E Fluid Nozzle, 704 Air Nozzle
Airless Spray	<i>Graco</i> - King 30:1 pump; 0.011-0.013" Fine Finish Tip

(Other equipment equivalent to the above may be used.)

Note: Certain colours may require more than one coat to achieve complete hiding of the substrate.

Gloss Reduction:

The gloss level of Regatta Gloss Enamel may be reduced by the addition of small amounts of AY&B Surfacer Undercoat. This is especially suitable for white and off white colours for interior use. We recommend trialling the ratio of the two components, starting with a 20% (v/v) addition of AY&B Surfacer Undercoat which will produce a soft semi-gloss.

For gloss reduction in darker, richer colours use Altex Flattening Paste – refer Flattening Paste Data Sheet for more details. Testing of the colour and degree of gloss reduction is strongly recommended.

Clean-up:

Use Altex Thinner #45 or #53

PRECAUTIONS

For DIY & Professional Use: Read and follow all the caution statements on this Product Data Sheet, the product label, and the Safety Data Sheet (SDS) for health and safety information prior to use.

Regatta Gloss Enamel is flammable. Keep away from heat, sparks, and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection

WWW.ALTEXBOATPAINT.COM

Head Office New Zealand

Altex Coatings Ltd
91-111 Oropi Road
Greerton, Tauranga 3112

Ph: +64 7 541 1221
Fax: +64 7 541 1310

Head Office Australia

**Resene Paints (Aust) Ltd
Industrial & Marine Division**
7 Production Avenue, Molendinar
Queensland 4214

Ph: +61 7 5512 6600
Fax: +61 7 5512 6697

DISCLAIMER

The information in this datasheet is provided as a guide only and is provided without warranty, implied or otherwise. It is your responsibility to determine the suitability of any information or product for the use contemplated. Conditions of use, application and the substrate are beyond our control so no liability whatsoever (whether as to coverage, performance, injury or otherwise) is accepted for the information contained herein.

Data sheets may change from time to time and it is your responsibility to ensure you have the latest product datasheet and material safety data sheet from your supplier. Check the data sheet date with the listings at www.altexcoatings.com. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.